



# SEAJET CLEAR COAT

## Product description

SEAJET CLEAR COAT is a foul-release coating for use on underwater lights, transducers and bow thrusters. Provides long term protection against fouling in both fresh and salt water environments. Fouling may loosely attach but is easily removed by water movement or washing (sponge).

## Product data

<b>Colour</b>	Clear
<b>Flash point</b>	56°C
<b>Volume solids %</b>	94 ±2
<b>VOC (Theoretical)</b>	51 g/l.
<b>Pack sizes</b>	250ml
<b>Mixing ratio</b>	One pack product

## Application details

<b>Thinner</b>	SEAJET THINNER A
<b>Application methods</b>	Brush, roller.
<b>Conditions</b>	Ambient temperature min. 5°C - max. 35°C Max. humidity 85% R.H. Product temperature min. 5°C - max. 35°C Substrate temperature min. 7°C - max. 35°C
<b>Spray details</b>	Nozzle tip Graco 619, 719 Paint output pressure: 17.7 - 20.6 MPa Thinning: 0 - 1 % (by volume)
<b>Spreading rate</b>	20,0 m <sup>2</sup> /l (theoretical)
<b>Recommended film thickness per coat</b>	Wet (µm) 50 Dry (µm) 47
<b>Substrates</b>	Glass or similar and suitable primed surfaces in case of bow thrusters.
<b>Preceding coating</b>	SEAJET 114 PROPELLER PRIMER (only for use on bow thrusters)
<b>Subsequent coating</b>	SEAJET CLEAR COAT
<b>Mixing</b>	Before use, stir thoroughly until product is mixed to a uniform consistency.

**Notes**

Warning: Due to the presence of silicon compounds, contamination of other areas. This can result in failure in those areas.  
Brushes and rollers should be dedicated or be thrown away.  
For the expectations of performance from this foul-release coating in static conditions: It is necessary to consider parameters such as trading pattern and the environmental conditions i.e., traditional level of fouling activity, pollution levels and water temperatures at static locations.  
\*In case of brush or roller application, more layers will be required to achieve the specified film thickness. Values are based on roller application.

## Surface preparation

When using for the first time: apply 2 coats SEAJET CLEAR COAT.  
For re-coating old SEAJET CLEAR COAT: remove fouling if any and clean by sponge.  
In case of bow thrusters repair the damaged areas by carefully abrading with P-180 abrasive paper. Thinner wipe the abraded area and touch up with SEAJET 114 PROPELLER PRIMER.  
Apply two fresh coats of SEAJET CLEAR COAT.  
SEAJET CLEAR COAT works differently from an antifouling, due to the special properties of the film, limiting the adhesion of fouling. SEAJET CLEAR COAT should only be repainted by itself.  
For removing any fouling growth a light pressure wash or cleaning by hose pipe and sponge is recommended. This will avoid damaging the coating and will leave it like new.



# SEAJET CLEAR COAT

## Drying / overcoating data

Temperature	Drying time (at DFT 45 µ)	Overcoating interval (at DFT 45 µ)	Induction time	Pot life	Dry to launch	Remarks
5 °C	Surface dry: 50 min Hard dry: 8 hours	Min.: 50 min Max.: None	-	-	12 hours	-
10 °C	Surface dry: 40 min Hard dry: 6 hours	Min.: 40 min Max.: None	-	-	10 hours	-
20 °C	Surface dry: 30 min Hard dry: 5 hours	Min.: 30 min Max.: None	-	-	8 hours	-
30 °C	Surface dry: 20 min Hard dry: 4 hours	Min.: 20 min Max.: None	-	-	7 hours	-

Notes: Drying times and overcoating intervals will increase with increasing film thickness applied.  
Before re-coating, always check that the existing paint film is 'through' dry.

## General information

### Storage

Store the containers in a dry, cool and well ventilated space and away from direct sunlight. Containers must be kept firmly closed. Handle with care.

### Transportation

The product should stay in a securely closed container during transport.

### Shelf life

Min. 2 years @ 20°C

### Disposal

Do not empty into drains, dispose of this material and its container at hazardous or special waste collection point.

### Additional information

More information can be found on [www.seajetpaint.com](http://www.seajetpaint.com).

## Safety information

Personal Protection advice and additional information can be obtained from the product Safety Data Sheet from Chugoku Paints B.V. which is available on request. The minimum safety precautions in dealing with this paint are:

- Observe the precautionary notices displayed on the container.
- Provide adequate ventilation.
- Avoid skin contact and inhalation of spray mist and vapours.
- If the product comes into contact with the skin, wash thoroughly with luke warm water and soap or suitable cleaner. If the eyes are contaminated, irrigate with water and seek medical advice immediately.
- Since the product contains flammable materials, keep away from sparks and open flames. No smoking should be permitted in the area.

## Disclaimer

Data, specifications, directions and recommendations given in this data sheet represent test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use is not guaranteed and must be determined by user. Product data is subject to change without notice and automatically void two years from issue. All legal relations of Chugoku Paints B.V. will be governed by the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. as last filed with the district court of Rotterdam and upon request they will be made available without charge. Chugoku Paints B.V. explicitly rejects the applicability of any General Conditions, which its contractual parties may use. Exclusive jurisdiction: competent Court in Rotterdam. Some products have been specially modified to adapt to specific European requirements with regard to European-, national- and local laws and regulations or with regards to specific European use requirements. As a result some physical properties in a TDS may differ from those given in the original Japanese TDS.