

# Epifanes Rust Remover

## Waterbased rust converter

<b>Description</b>	Product for removing rust in difficult areas on steel surfaces
<b>Type</b>	Water repelling polymeres
<b>Properties</b>	Creates a reaction with corroded steel, making the surface suitable for painting. Stops corrosion proces for some time.
<b>Field of application</b>	Removing rust in difficult places on manually derusted steel, i.e. in corners and in case of punctiform rusting. Suitable for use above and below the waterline.
<b>Colour</b>	Milky off white. After reaction steel looks blue/black
<b>Density</b>	1,02kg/dm³
<b>Ph value</b>	1,5
<b>VOC - level</b>	0,00 grams/litre
<b>Packing</b>	500 ml.
<b>Shelf life</b>	In closed container stored in a dark location between 5 - 25°C., At least 3 years. <b>Store frost free.</b>
<b>Conditions during application and drying</b>	Temperature min. 5°C - max 28°C. Relative air humidity min 50% - max 90% Temperature of surface to be treated must be 3°C. above freezing
<b>Application tools</b>	Brush - roller - spray
<b>Application instructions</b>	Remove all loose rust by wire brush and/or coarse abrasive paper P40-60. Make sure the entire bare steel surace is coarsely abraded. Hose the surface with fresh water to remove remaining contamination. Finally well degrease the surface with Epifanes Cleaning Solution.  Shake well prior to use and apply one thin coat Epifanes Rust Remover. The Rust Remover quickly reacts with rust changing these areas into a blue/black surface.  Epifanes Rust Remover may be applied on wet steel and under humid conditions with limited ventilation.
<b>Drying times</b>	Between min. 3 hours and max. 2 days the blue/black surface may be painted with the first (thinned) anticorrosive primer.
<b>Recoatability</b>	With all Epifanes one-and twocomponent primers/coatings
<b>Remarks</b>	The rust remover must react with rust. Do not apply on (parts of) primers/ paints/coatings. If spilled on paint or primer, remove the Rust Remover by cloth as soon as possible One treatment is sufficient, do not repeat. - The Rust Remover is no replacement for a primer coat.
<b>Safety</b>	The user of this product should obey all national laws and legislation concerning health, safety and environmental hazard. For more information on health and safety, refer to the Material Safety Data Sheet of this product.

Although the facts and suggestions in this product information sheet are based on our own research and field experiences and are believed reliable, we cannot simply be held responsible for performance or results obtained through the use of this product. Ineffectiveness or other unintended consequences may result, because of such factors as weather, conditions, presence or other materials or the manner of preparation, use or application all of which are beyond W. Heeren & Zoon's control. All such risks are assumed by user.

**DISCLAIMER OF WARRANTIES.** Seller makes no express warranties.

THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. In the event a warranty is created by law, buyer's EXCLUSIVE REMEDY shall be the replacement of any defective product. No other remedy ( including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or any other incidental or consequential loss ) shall be available to buyer.